

CERTIFICATE OF MAILING UNDER 37 C.F.R. §1.8

I hereby certify that this correspondence is being deposited with the United States Postal Service as first class mail, with sufficient postage, in an envelope addressed to: Commissioner for Patents, P. O. Box 1450, Alexandria, VA 22313-1450, on the below date:

Date: 06-1-2005 Name: Richard G. Lione, Reg. No. 19,795 Signature: Richard G. Lione

1714
RL

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Appln. of: **Kazuaki Matsumoto et al.**

Appln. No.: **10/031,210**

**BRINKS
HOFER
GILSON
& LIONE**

Filed: **January 11, 2002**

Examiner: **Peter A. Szekely**

Art Unit: **1714**

For: **FLAME RETARDANT AND FLAME-RETARDANT RESIN COMPOSITION**

Attorney Docket No: **5404/16**

Mail Stop Amendment
Commissioner for Patents
P. O. Box 1450
Alexandria, VA 22313-1450

TRANSMITTAL

Sir:

Attached is/are:

- ☒ Transmittal (in Duplicate); and English Translation of the Priority Application (JP 2000-138974).
- ☒ Return Receipt Postcard

Fee calculation:

- ☒ No additional fee is required.
- ☐ Small Entity.
- ☐ An extension fee in an amount of \$_____ for a _____-month extension of time under 37 C.F.R. § 1.136(a).
- ☐ A petition or processing fee in an amount of \$_____ under 37 C.F.R. § 1.17(_____).
- ☐ An additional filing fee has been calculated as shown below:

					Small Entity			Not a Small Entity	
	Claims Remaining After Amendment		Highest No. Previously Paid For	Present Extra	Rate	Add'l Fee	or	Rate	Add'l Fee
Total		Minus			x \$25=			x \$50=	
Indep.		Minus			x 100=			x \$200=	
First Presentation of Multiple Dep. Claim					+\$180=			+\$360=	
					Total	\$		Total	\$

Fee payment:

- ☐ A check in the amount of \$_____ is enclosed.
- ☐ Please charge Deposit Account No. 23-1925 in the amount of \$_____. A copy of this Transmittal is enclosed for this purpose.
- ☐ Payment by credit card in the amount of \$_____ (Form PTO-2038 is attached).
- ☒ The Director is hereby authorized to charge payment of any additional filing fees required under 37 CFR § 1.16 and any patent application processing fees under 37 CFR § 1.17 associated with this paper (including any extension fee required to ensure that this paper is timely filed), or to credit any overpayment, to Deposit Account No. 23-1925.

June 1, 2005
Date

Respectfully submitted,

Richard G. Lione
Richard G. Lione (Reg. No. 19,795)


VERIFICATION OF TRANSLATION



I, Yasuo Yasutomi of Chuo BLDG., 4-20, Nishinakajima 5-chome,
Yodogawa-ku, Osaka-shi, Osaka 532-0011 JAPAN, hereby declare that I am
conversant with the Japanese and English languages and that I am the
translator of the documents attached and certify that to the best of
my knowledge and belief the following is a true and correct English
translation of the Japanese Patent Application No. 2000-138974
in the name of KANEKA CORPORATION.

Dated this 26th day of May,

2005



Yasuo Yasutomi

[Document Name] Patent Application
[Filing Number] KEN-3938
[To] Commissioner, Patent Office
[IPC] C08G 77/04
[Inventor]
[Address or Residence] 5-111, Kitakinomoto, Yao-shi, Osaka
[Name] MATSUMOTO Kazuaki
[Inventor]
[Address or Residence] 13-13-105, Mishima 2-chome, Settsu-shi,
Osaka
[Name] ONO Yoshiki
[Inventor]
[Address or Residence] 9-9, Shinryodai 7-chome, Tarumi-ku,
Kobe-shi, Hyogo
[Name] YOSHIDA Ryuji
[Applicant]
[Identification Number] 000000941
[Name] KANEKA CORPORATION
[Agent]
[Identification Number] 100086586
[Patent attorney]
[Name] YASUTOMI Yasuo
[Designated Agent]
[Identification Number] 100104813
[Patent Attorney]
[Name] FURUTANI Shinya
[Designated Agent]
[Identification Number] 100108431
[Patent Attorney]
[Name] MURAKAMI Kanako
[Indication of Fee]
[Number of Deposit Ledger] 033891
[The Amount of Payment] 21,000 yen
[List of Attached Documents]
[Document Name] Description 1



2

[Document Name]	Drawings	1
[Document Name]	Abstract	1
[Number of general power of attorney]		9705256
[Necessity of Proof]	Needed	

[Document Name] Description

[Title of the Invention] FLAME RETARDANT AND FLAME-RETARDANT RESIN COMPOSITION


[Scope of Claims for Patent]

5 [Claim 1] A flame retardant comprising an aromatic group-containing organosiloxane compound

wherein said compound has the following mean composition formula (1),

does not flow at 23°C,
10 flows at 200°C,
does not gelate when heated at 200°C with stirring for 30 minutes, and

has a number average molecular weight of not less than 2,000 and at the same time, dissolves not less than
15 100 g in 1 L of a solvent toluene at 23°C:



in the formula, R¹ represents a univalent aliphatic hydrocarbon group containing 1 to 4 carbon atoms; R² represents a univalent aromatic hydrocarbon group
20 containing 6 to 24 carbon atoms; R¹ and R² each may contain two or more species; and m and n are numbers satisfying $1.1 \leq m + n \leq 1.7$ and $0.4 \leq n/m \leq 2.5$.

[Claim 2] A flame retardant resin composition

which comprises 0.2 to 20 parts by weight of the
25 flame retardant (A) comprising an aromatic group-containing organosiloxane compound according to Claim 1 relative to 100 parts by weight of a resin (B) having an oxygen or sulfur atom and an aromatic ring within the molecule thereof.

30 [Claim 3] The flame retardant resin composition according to Claim 2,

wherein the aromatic group-containing organosiloxane compound (A) is dispersed with the number average dispersed particle diameter within the range of 0.01 μm to 0.5 μm in
35 the resin (B) having an oxygen or sulfur atom and an

aromatic ring within the molecule thereof.

[Detailed Description of the Invention]

[0001]

[Technical Field of the Invention]

5 The present invention relates to a flame retardant comprising an organosiloxane compound having a specific composition and a flame retardant resin composition rendered flame retardancy by that flame retardant.

[0002]

10 [Prior Art]

Flame retardant resin compositions are utilized in various fields, such as electric and electronic fields and building material fields, for ensuring the safety from fire. In these resin compositions, halogen compounds, such as
15 chlorine compounds or bromine compounds, have generally been used as flame retardants. In view of the recent increasing concern about environmental problems in European and other countries, various investigations have been made about the use of phosphorus-containing flame retardants and
20 other halogen-free flame retardants.

However, when phosphorus-containing flame retardants such as phosphate ester compounds, red phosphorus and the like are used for attaining flame retardancy, there have been problems such that odors may emanate in the extrusion
25 or molding step and the mechanical characteristics and thermal characteristics may be adversely affected. Therefore, various materials have been tested in search of flame retardants capable of taking the place of halogen compounds and phosphorus compounds.

30 [0003]

Silicone compounds are known as halogen-free, phosphorus-free flame retardants. Thus, Japanese Kokai Publication Sho-54-36365 discloses a resin composition comprising a non-silicone polymer rendered flame retardancy
35 with a silsesquioxane mainly comprising T units, and

Japanese Kokai Publication Hei-10-139964 discloses a resin composition comprising an aromatic ring-containing non-silicone resin rendered flame retardancy with a silicone resin having T and D units.

5 [0004]

[Subject which the Invention is to Solve]

However, in the silsesquioxane resin disclosed in Japanese Kokai Publication Sho-54-36365, an expensive silsesquioxane resin is required to be added in a large amount for attaining flame retardancy, hence it is impractical. The silicone resin described in Japanese Kokai Publication Hei-10-139964 is effective for polycarbonates but has little effect in rendering other resins flame retardancy, hence cannot provide them with a sufficient level of flame retardancy.

15

[0005]

[Means for Solving the Problems]

The present inventors made various investigations on silicone compounds having various compositions and, as a result, succeeded in synthesizing silicone compounds highly effective in attaining flame retardancy at low addition levels by strictly controlling the composition of the silicone compound to be used as a flame retardant and they have now completed the present invention.

20

[0006]

Thus, the present invention is concerned with a flame retardant comprising an aromatic group-containing organosiloxane compound

wherein said compound has the following mean
30 composition formula (1),

does not flow at 23°C,

flows at 200°C,


does not gelate when heated at 200°C with stirring for 30 minutes, and

35

has a number average molecular weight of not less

than 2,000 and at the same time, dissolves not less than 100 g in 1 L of a solvent toluene at 23°C, as well as a flame retardant resin composition

comprising 0.2 to 20 parts by weight of the above
5 flame retardant (A) relative to 100 parts by weight of a resin (B) having an oxygen or sulfur atom and an aromatic ring within the molecule thereof:



in the formula, R^1 represents a univalent aliphatic
10 hydrocarbon group containing 1 to 4 carbon atoms and R^2 represents a univalent aromatic hydrocarbon group containing 6 to 24 carbon atoms. R^1 and R^2 each may contain two or more species. m and n are numbers satisfying $1.1 \leq m + n \leq 1.7$ and $0.4 \leq n/m \leq 2.5$.

15 In the following, the present invention is described in detail.

[0007]


[Embodiment of the Invention]

The flame retardant of the invention comprises an
20 aromatic group-containing organosiloxane compound. The aromatic ring-containing organosiloxane compound is a polymer formed from at least one of the four constituent units, namely the Q unit (SiO_2), T unit ($RSiO_{1.5}$), D unit (R_2SiO) and M unit ($R_3SiO_{0.5}$), wherein R represents an
25 aromatic hydrocarbon group and/or an aliphatic hydrocarbon group.

[0008]

The aromatic group-containing organosiloxane compound according to the present invention satisfies all the
30 following requirements (1) to (5).

(1) It has the following mean composition formula (1):



in the formula, R^1 represents a univalent aliphatic
hydrocarbon group containing 1 to 4 carbon atoms and R^2
35 represents a univalent aromatic hydrocarbon group

containing 6 to 24 carbon atoms. R^1 and R^2 each may contain two or more species. m and n are numbers satisfying $1.1 \leq m + n \leq 1.7$ and $0.4 \leq n/m \leq 2.5$.

(2) It does not flow at 23°C.

5 (3) It flows at 200°C.

(4) It does not gelate when heated at 200°C with stirring for 30 minutes.

(5) It has a number average molecular weight of not less than 2,000 and at the same time, dissolves not less than
10 100 g in 1 liter of toluene at 23°C.

In the following, these are described one by one.

[0009]

(1) That "it has the mean composition formula (1)" means that the aromatic group-containing organosiloxane
15 compound meets the following requirements. Thus, it has both the univalent aliphatic hydrocarbon group R^1 containing 1 to 4 carbon atoms and the univalent aromatic hydrocarbon group R^2 containing 6 to 24 carbon atoms within the molecule thereof, that the mole ratio $m + n$ between all
20 these hydrocarbon groups and the number of Si atoms is within the range of $1.1 \leq m + n \leq 1.7$ and that the mole ratio n/m between the univalent aliphatic hydrocarbon group R^1 containing 1 to 4 carbon atoms and the univalent aromatic hydrocarbon group R^2 containing 6 to 24 carbon
25 atoms is within the range of $0.4 \leq n/m \leq 2.5$. The proportions of each element and each hydrocarbon group are calculated based on the NMR for hydrogen, carbon and silicon.

[0010]

30 The aliphatic hydrocarbon group R^1 containing 1 to 4 carbon atoms is not particularly restricted but there may be specifically mentioned, for example, methyl, ethyl, n-propyl, isopropyl, n-butyl, sec-butyl, tert-butyl and like groups. Among these, methyl and ethyl groups are preferred
35 because of good flame retardant effects, and methyl group

is more preferred. The plurality of R^1 may be all the same or may contain different groups. When the number of carbon atoms in the aliphatic hydrocarbon group is 5 or more, the flame retardant effects of the aromatic group-containing organosiloxane compound itself decrease, hence the flame retardant effects decrease.

[0011]

The univalent aromatic hydrocarbon group R^2 containing 6 to 24 carbon atoms is not particularly restricted but there may be specifically mentioned, for example, phenyl, methylphenyl, dimethylphenyl, ethylphenyl, naphthyl, anthracenyl and like groups. Among these, aromatic groups having no substituent on the aromatic ring are preferred because of good flame retardant effects. Phenyl group is more preferred. The plurality of R^2 may be all the same or may contain different groups.

[0012]

The mole ratio $m + n$ between all the hydrocarbon groups and the number of Si atom is within the range of $1.1 \leq m + n \leq 1.7$. The value of $m + n$ is preferably within the range of $1.15 \leq m + n \leq 1.65$, more preferably $1.18 \leq m + n \leq 1.6$, still more preferably $1.20 \leq m + n \leq 1.55$. A value of $m + n$ which is less than 1.1 or more than 1.7 is not preferable since the flame retardant effect of the aromatic group-containing organosiloxane compound decreases.

[0013]

For the aromatic group-containing organosiloxane compound according to the present invention to meet the above requirements (2) to (5), it is generally necessary that the compound contain a considerable proportion of the M unit within the molecule thereof. Therefore, for obtaining a composition satisfying the relation $1.1 \leq m + n \leq 1.7$, a structure mainly comprising the T unit in addition to the M unit is preferred. In cases where the D unit occurs, it is possible to obtain a composition

satisfying the relation $1.1 \leq m + n \leq 1.7$ by causing the Q unit to occur.

[0014]

The mole ratio n/m between the univalent aliphatic hydrocarbon group R^1 containing 1 to 4 carbon atoms and the univalent aromatic hydrocarbon group R^2 containing 6 to 24 carbon atoms is within the range of $0.4 \leq n/m \leq 2.5$. When n/m is less than 0.4, the univalent aliphatic hydrocarbon group R^1 becomes abundant within the molecule and, on that occasion, the heat resistance of the aromatic group-containing organosiloxane compound decreases, so that compounds occurring as liquids at room temperature may easily be obtained, and/or the flame retardancy of the aromatic group-containing organosiloxane compound itself lowers, thus decreasing the flame retardant effects of the aromatic group-containing organosiloxane compound may be caused. When n/m is not less than 2.5, the univalent aromatic hydrocarbon group R^2 becomes abundant within the molecule and, on that occasion, the heat resistance of the aromatic group-containing organosiloxane compound will be excessively improved, so that compounds occurring as solids at 200°C or as liquids having a very high viscosity may be obtained, thus decreasing flame retardant effects of the aromatic group-containing organosiloxane compound may be caused. The value of n/m is preferably $0.43 \leq n/m \leq 2.3$, more preferably $0.45 \leq n/m \leq 2.1$, still more preferably $0.47 \leq n/m \leq 2.0$.

[0015]

Further, the value of n/m generally causes a change in the dispersibility of the aromatic group-containing organosiloxane compound in resins. Although the value of n/m for obtaining the optimum dispersibility may vary according to the resin species, the dispersibility of the aromatic group-containing organosiloxane compound can be improved and high flame retardant effects can be obtained

by selecting a higher value of n/m within the above range when the proportion of aromatic rings occurring in the resin employed is large, or by selecting a lower value of n/m within the above range when the proportion of aromatic rings occurring in the resin is small.
[0016]

(2) That it does not flow at 23°C is important in attaining good and uniform dispersibility of the aromatic group-containing organosiloxane compound in a resin when the aromatic group-containing organosiloxane compound is admixed with the resin. If it flows at 23°C, the aromatic group-containing organosiloxane compound will hardly occur uniformly in the resin or will be unevenly distributed or a continuous organosiloxane phase may occur, so that the flame retardancy of the composition obtained will be deteriorated. The term "flows" means that this compound occurs as a liquid at the given temperature. According to the composition and/or molecular weight of this compound, it is difficult in some cases to judge as to whether this compound is a liquid or a solid. In cases where it is difficult to judge as to whether it is a liquid or a solid, the judgment based on the following judgment criterion is employed. Thus, 10 g of this sample is taken and finely ground to thereby prepare a powder form so that all particles may have a particle diameter of not more than 1 mm. This powder is maintained at the temperature for fluidity judgment in a glass container, and after 10 minutes of standing, the state of this compound is again observed. When the whole amount of this compound is found as a state of coalescent and fixed, the judgment "flows" was given. It is more preferred that the compound be a solid having no tackiness at 23°C.
[0017]

As the general method of obtaining the aromatic group-containing organosiloxane compound as a compound not

flowing at 23°C, there may be mentioned the method which comprises selecting the mole ratio $m + n$ between all hydrocarbon groups and Si atoms at a lower level within the range of $1.1 \leq m + n \leq 1.7$, the method which comprises
5 selecting the mole ratio n/m between the univalent aliphatic hydrocarbon group R^1 containing 1 to 4 carbon atoms and the univalent aromatic hydrocarbon group R^2 containing 6 to 24 carbon atoms at a higher level within the range of $0.4 \leq n/m \leq 2.5$ and the method which
10 comprises selecting the molecular weight of the aromatic group-containing organosiloxane compound at a level as high as possible within the preferred range.

[0018]

(3) The aromatic group-containing organosiloxane
15 compound is a compound flowing at 200°C. Those organosiloxane compounds which will not flow at 200°C have almost no substantial flame retardant effects. For obtaining good flame retardancy, the compound preferably flows at not lower than 170°C, more preferably flows at not
20 lower than 150°C. Furthermore, it is preferred that the compound has a low melt viscosity as measured at 200°C, since then the flame retardancy is improved. The viscosity measured at 200°C is preferably not more than 1,000,000 cSt, more preferably not more than 100,000 cSt, most preferably
25 not more than 10,000 cSt.

[0019]

As the general method of obtaining the aromatic group-containing organosiloxane compound as a compound flowing at 200°C, there may be mentioned the method which
30 comprises selecting the mole ratio $m + n$ between all hydrocarbon groups and Si atoms at a higher level within the range of $1.1 \leq m + n \leq 1.7$, the method which comprises selecting the mole ratio n/m between the univalent aliphatic hydrocarbon group R^1 containing 1 to 4 carbon
35 atoms and the univalent aromatic hydrocarbon group R^2

containing 6 to 24 carbon atoms at a lower level within the range of $0.4 \leq n/m \leq 2.5$ and the method which comprises selecting the molecular weight of the aromatic group-containing organosiloxane compound at a level as low as possible within the range mentioned later herein.
[0020]

(4) The aromatic group-containing organosiloxane compound is a compound which will not gelate when heated at 200°C with stirring for 30 minutes. Those organosiloxane compounds which gelate in less than 30 minutes when heated at 200°C with stirring have almost no flame retardant effects. It is preferred that the compound will not gelate when heated at 200°C with stirring for 60 minutes and it is more preferred that it will not gelate when heated at 200°C with stirring for 120 minutes. The judgment about "gelation" is made in the following manner. The 200 g of powdery sample being stirred at the temperature for gelation judgment under vacuum for the designated period followed by being cooled to 23°C and ground is placed in 1 L of toluene at 23°C and after 24 hours of stirring at 23°C, the insoluble matter was filtered off. The filtered component is dried under vacuum at 23°C for 6 hours and then weighed. When the weight of the insoluble matter is not less than 100 g, it is judged as gelated. If, however, an acidic or alkaline compound, a catalyst decomposing silicones and the like are coexist in the step of heating and stirring, even a preferred aromatic group-containing organosiloxane compound may gelate in some cases. Therefore, it is necessary to carry out this test under conditions substantially free of such impurities.
[0021]

As the general method of obtaining the aromatic group-containing organosiloxane compound as one which will not gelate when heated at 200°C with stirring for 30 minutes, there may be mentioned the method which comprises

reducing, as far as possible, the amount of reactive groups occurring within the molecule of the aromatic group-containing organosiloxane compound. The reactive groups mentioned above include such condensable groups as silanol and alkoxysilyl groups. When the reactive groups are present within the molecule, these reactive groups react with one another in the step of heating and stirring, thus tending to cause gelation.

[0022]

- 10 (5) The aromatic group-containing organosiloxane compound is a compound which has a number average molecular weight of not less than 2,000 and at the same time, dissolves not less than 100 g in 1 L of a solvent toluene at 23°C. The number average molecular weight so referred to herein is the value obtained by converting the measured value as measured by using a conventional GPC molecular weight measuring apparatus with chloroform as the solvent and an RI detector to a value based on the measured value for a polystyrene species having a known molecular weight.
- 15 Excessively high or excessively low number average molecular weights are not preferred. If the number average molecular weight is less than 2,000, the heat stability of the aromatic group-containing organosiloxane compound itself decreases, hence the flame retardancy decreases.
- 20 The solubility in solvents of the aromatic group-containing organosiloxane compound lowers as the molecular weight increases. In order to provide resins with flame retardancy, the aromatic group-containing organosiloxane compound is required to have a solubility of not less than
- 25 100 g in 1 L of a solvent toluene at 23°C. Those high-molecular weight ones which are insoluble in solvents show almost no flame retardancy when added to the resin. The number average molecular weight is preferably within the range of 2,400 to 50,000, more preferably 2,700 to 10,000,
- 30 still more preferably 2,900 to 7,000.
- 35

[0023]

Such aromatic group-containing organosiloxane compound can be synthesized easily by a known silicone synthesizing method. Thus, it can be synthesized by
5 subjecting at least one, preferably at least two silicon compounds selected, according to need, from among monofunctional silicon compounds represented by R_3SiX , bifunctional silicon compounds represented by R_2SiX_2 , trifunctional silicon compounds represented by $RSiX_3$ and
10 tetrafunctional silicon compounds such as silicon tetrahalides, tetraalkoxysilanes, water glass and metal silicates to condensation reaction. In the formulas, R represents an aromatic hydrocarbon group or an aliphatic hydrocarbon group, and X represents a group capable of
15 forming a siloxane bond upon condensation, such as a halogen, a hydroxyl group or an alkoxy group.

[0024]

The reaction conditions vary according to the substrate to be employed and the composition and molecular
20 weight of the desired compound. Generally, the reaction can be carried out by mixing the silicon compounds, if necessary in the presence of water, an acid and/or an organic solvent, if necessary with heating. The proportions of the respective silicon compounds to be used
25 can appropriately be selected taking into consideration the contents of the respective units and the ratio between the aromatic hydrocarbon group and the aliphatic hydrocarbon group so that the aromatic group-containing organosiloxane compound to be obtained may meet the requirements mentioned
30 above. For reducing the amount of reactive groups occurred as far as possible, as mentioned above, it is preferable to add, after the above condensation reaction, a monofunctional silicon compound represented by R_3SiX in excessive amount and conduct condensation reaction.

35 [0025]

The resin (B) having an oxygen or sulfur atom and an aromatic ring within the molecule thereof, which is to be used in accordance with the present invention, may be a synthesized one or a natural resin. It may be any of a thermoplastic resin and a thermosetting resin. A thermoplastic resin is preferred since the flame retardancy of the flame retardant resin composition is improved.
[0026]

As such resin, there are various species.
Particularly suited are, for example, aromatic polycarbonate resins, aromatic polyester resins, polyarylate resins, aromatic polyamide resins, aromatic vinyl/alkyl (meth)acrylate copolymer resins, aromatic vinyl/maleic anhydride copolymer resins, aromatic vinyl/alkyl (meth)acrylate/rubber-like polymer copolymer resins, N-phenylmaleimide resins, polyphenylene ether resins, aromatic polyetherketone resins, aromatic polyketone resins, polyphenylene sulfide resins, phenolic resins, aromatic epoxy resins, aromatic phenoxy resins and the like. These resins having an oxygen or sulfur atom and an aromatic ring within the molecule thereof may be used singly or two or more species may be used in combination.
[0027]

The resin may be the mixture of the resin having an oxygen or sulfur atom and an aromatic ring within the molecule thereof with another resin. The resin to be admixed with the resin having an oxygen or sulfur atom and an aromatic ring within the molecule thereof is not particularly restricted but various resins in general use can be used. In cases where the resin is the mixture of the resin having an oxygen or sulfur atom and an aromatic ring within the molecule thereof with another resin species, the mixing ration between them, namely the ratio (resin having an oxygen or sulfur atom and an aromatic ring within the molecule)/(other resins), is preferably not less than

0.3, more preferably not less than 0.5, still more preferably not less than 1.0.

[0028]

The level of addition of the aromatic group-
5 containing organosiloxane compound for attaining good flame retardancy is 0.2 to 20 parts by weight relative to the resin. The preferred level of addition is 0.3 to 15 parts by weight, more preferred level of addition is 0.5 to 10 parts by weight. If the level of addition is less than 0.2
10 part by weight, the composition obtained will not show a satisfactory level of flame retardancy. If the level of addition exceeds 20 parts by weight, the composition will generally become economically disadvantageous, although, in most cases, no problems arise from the physical
15 characteristics viewpoint.

[0029]

In the resin composition added with the flame retardant of the present invention, the aromatic group-containing organosiloxane compound is preferably dispersed,
20 in the resin having an oxygen or sulfur atom and an aromatic ring within the molecule thereof, as particles having a number average dispersed particle diameter within the range of 0.01 μm to 0.5 μm . Owing to the fact that the aromatic group-containing organosiloxane compound has the
25 structure such as mentioned hereinabove, it becomes possible to disperse the organosiloxane compound within such a range. By being dispersed in such a minute particle form, the compound can show very good flame retardancy. The number average dispersed particle diameter so referred
30 to herein is the value calculated on the number average basis from the diameters of dispersed particles of the aromatic group-containing organosiloxane compound as calculated regarding the relative particles as circular upon observation, under a transmission electron microscope
35 at a magnification of about 16,000 times, of approximately

the middle portion in the direction of thickness of the molding having a thickness of 3.2 mm as molded from the resin composition obtained. The number average dispersed particle diameter is more preferably within the range of 0.02 μm to 0.4 μm , still more preferably within the range of 0.03 μm to 0.3 μm . The number average dispersed particle diameter is influenced by the level of addition of the aromatic group-containing organosiloxane compound and the dispersed particle diameter tends to increase with the increased level of addition thereof.

[0030]

In the flame retardant resin composition of the present invention, there may be incorporated a fluororesin and/or a silicon-containing polymer other than the aromatic group-containing organosiloxane compound to be used according to the invention, for further increasing the flame retardancy.

[0031]

The fluororesin is a resin containing a fluorine atom(s) therein. Specifically, there may be mentioned polymonofluoroethylene, polydifluoroethylene, polytrifluoroethylene, polytetrafluoroethylene, tetrafluoroethylene/hexafluoropropylene copolymers and the like. If necessary, copolymers obtained by copolymerizing a monomer(s) to be used in the production of the above fluororesins with another monomer copolymerizable therewith may also be used unless the flame retardancy and other physical properties of the moldings obtained are impaired. These fluororesins are used singly or in combination of two or more species. The fluororesins preferably have a molecular weight of 1,000,000 to 20,000,000, more preferably 2,000,000 to 10,000,000. As for the production method of these fluororesins, they can be obtained by such generally known methods as emulsion polymerization, suspension polymerization, bulk polymerization and solution

polymerization.

[0032]

The silicon-containing polymer other than the aromatic group-containing organosiloxane compound to be used in accordance with the present invention includes diorganosiloxane compounds such as dimethylsiloxane and phenylmethylsiloxane, organosilhemioxane compounds such as trimethylsilhemioxane and triphenylsilhemioxane, and copolymers obtainable by polymerizing these, polydimethylsiloxane, polyphenylmethylsiloxane, polysilanes, polycarbosilanes, polysilazanes, silicon-boron copolymers, silicon-metal copolymers and so on. Modified silicon polymers derived by substitution of epoxy, hydroxyl, carboxyl, mercapto or amino group, ether or the like in part of the molecule may also be used. Among others, the polymer is preferably one having a number average molecular weight not less than 200, more preferably having a number average molecular weight within the range of 1,000 to 5,000,000 since such polymer can more improve the flame retardancy. The form of the silicone is not particularly restricted but any arbitrary form such as an oil, gum, wax, powder or pellets can be utilized. Among them, silicon-boron copolymers are preferred since they are effective in markedly increasing the flame retardant effects.

[0033]

The level of addition of the fluororesin and/or silicon-containing polymer is not particularly restricted unless the characteristics (chemical resistance, heat resistance, etc.) attainable in accordance with the present invention are not impaired. Preferably, however, it is 0.01 to 10 parts by weight, more preferably 0.03 to 8 parts by weight, particularly preferably 0.05 to 6 parts by weight, relative to 100 parts by weight of the resin. If the level of addition is below 0.01, the effect of improving flame retardancy will be slight and, If it

exceeds 10 parts by weight, the moldability may decrease in some instances.

[0034]

For obtaining the flame retardant resin composition
5 of the present invention as a composition of higher performance, one or a combination of two or more of heat stabilizers, such as phenolic stabilizers, thioether stabilizers and phosphorus-containing stabilizers, is preferably used. Further, according to need, one or a
10 combination of two or more of generally well-known additives such as lubricants, mold release agents, plasticizers, flame retardants, flame retardant auxiliaries, ultraviolet absorbers, light stabilizers, pigments, dyes, antistatic agents, conductivity providing agents,
15 dispersants, compatibilizing agents and antimicrobial agents may be used. However, when, as such additives, ones capable of promoting the decomposition or reaction of the aromatic group-containing organosiloxane compound is used, the flame retardancy of the resulting composition will
20 decrease. So, the use of such compounds is not preferred.
[0035]

The production method of the composition of the present invention is not particularly restricted. For example, it can be produced by melt kneading the above
25 components together with the other additive(s), resin(s) and so forth, if necessary after drying, in a melt kneading machine such as a single screw or twin screw extruder. For dispersing the aromatic group-containing organosiloxane compound within the number average dispersed particle
30 diameter range of 0.01 μm to 0.5 μm in the resin, it can be produced by the method comprising kneading while exerting a shear force in the molten state with the use of a melt kneading machine, specifically, as a twin screw extruder.

The method of molding the flame retardant resin
35 composition produced according to the present invention is

not particularly restricted but those molding techniques in general use, for example injection molding, blow molding, extrusion molding, vacuum molding, press molding, calendaring, foam molding and other techniques, can be
5 applied.

The flame retardant resin composition of the present invention is suitably used in various uses. Preferred fields of use include household electric appliances, OA equipment, automotive parts and other injection-molded
10 articles, blow-molded articles, extrusion-molded articles, expansion-molded articles and so forth.

[0036]

[Examples]

The following examples illustrate the present
15 invention in more detail. They are, however, by no means limitative of the scope of the present invention. In the following, unless otherwise specified, "part(s)" denotes "part(s) by weight" and "%" denotes "% by weight".

The resin compositions were evaluated by the
20 following methods.

The aromatic group-containing organosiloxane compound was analyzed using the following methods.

[0037]

Mean composition formula:

25 The sample was dissolved in deuteriochloroform as the solvent and the proportions of hydrogen, carbon and silicon were calculated based on the NMR data.

Fluidity:

When the compound evidently occurred as a liquid at
30 23°C or 200°C, it was regarded as "fluid". When it was difficult to judge as to whether the compound occurred as a liquid or a solid at each temperature, the following procedure was followed for judgment. Thus, 10 g of each sample was taken and finely ground to thereby prepare a
35 powder form so that all particles may have a particle

diameter of not larger than 1 mm. This powder was maintained at the temperature for fluidity judgment in a glass container and, after 10 minutes of standing, the state of this compound was again observed. When this compound was found as a state of coalescent and fixed, the judgment "fluid" was given. When this compound remained in a powdery form or found partially fixed but the whole sample was not found coalescent, the judgment "nonfluid" was given.

10 [0038]

Solubility in 1 L of toluene at 23°C:

Into 1 L of toluene was poured 200 g of the sample in powder form after 6 hours of drying at 23°C under vacuum and, after 24 hours of stirring at 23°C, the insoluble matter was filtered off. The component filtered off was dried at 23°C under vacuum for 6 hours and then weighed. The solubility was calculated according to the formula $200 - (\text{insoluble matter weight})$. For the samples which gave no insoluble matter at all, the solubility was reported as >200 g.

20 [0039]

Gelation at 200°C:

The 200 g of the powdery sample being stirred at 200°C under vacuum for 30 minutes followed by being cooled to 23°C and ground was placed in 1 L of toluene at 23°C and, after 24 hours of stirring at 23°C, the insoluble matter was filtered off. The component filtered off was dried at 23°C under vacuum for 6 hours and then weighed. When the weight of the insoluble matter was not less than 100 g, the judgment "gelation" was given. For the samples not given the judgment "gelation" in the above examination, the same test was performed by prolonging the time of heating at 200°C to 60 minutes and then to 120 minutes successively. When gelation occurred after 60 minutes of stirring, the judgment "gelation after 60 minutes" was given and, when

gelation occurred after 120 minutes of stirring, the judgment "gelation after 120 minutes" was given. The samples showing no gelation even after 120 minutes of stirring were given the judgment "no gelation". When the solubility was found not more than 100 g in the test for "solubility in 1 L of toluene at 23°C", this test was not performed.

[0040]

Number average molecular weight:

10 The number average molecular weight was calculated after performing detection with RI detector under the following conditions: Waters model 510 type GPC system, column: Shodex K-80M, K-802.5, column temperature 35°C, mobile phase: chloroform (for HPLC; product of Wako Pure
15 Chemical), flow rate: 1 mL/min, injection size: 50 µL (about 0.3 wt%), standard sample; polystyrene (Shodex Standard; product of Showa Denko). At the same time, the weight average molecular weight was also calculated, and the molecular weight distribution was calculated according
20 to the formula (weight average molecular weight)/(number average molecular weight). When a sample was insoluble in the chloroform solvent, the above analysis was not performed but only the evaluation of measuring solubility in toluene at 23°C was carried out.

25 [0041]

(Production Example 1): Production of an aromatic group-containing organosiloxane compound (A1)

 Tetrachlorosilane (1.0 part), 12.0 parts of methyltrichlorosilane, 64.0 parts of phenyltrichlorosilane
30 and 200 parts of methyl isobutyl ketone as solvent were charged into a reaction vessel with ice cooling, and 75 parts of ion-exchange water was added gradually with stirring over 6 hours while adjusting the temperature within the range of 0 to 10°C. After completion of the
35 addition, the mixture was stirred at room temperature for

12 hours and, then, 23.0 parts of trimethylchlorosilane was added dropwise at room temperature. The mixture was stirred at room temperature for 12 hours. The mixture was washed with water until the washings of the resin became neutral. The organic phase separated was deprived of the solvent and low-molecular byproducts by evaporation, to give an aromatic group-containing organosiloxane compound (A1) as a solid.

[0042]

- 10 (Production Example 2): Production of an aromatic group-containing organosiloxane compound (A2)

A reaction vessel was charged with 1.16 moles of phenyltrimethoxysilane, 0.58 mole of tetraethoxysilane, 4.93 moles of pure water and 40 ppm of 35% hydrochloric acid, and the mixture was stirred at 23°C for 1 hour, then at 40°C for 1 hour and finally at 60°C for 1 hour.

- 15 Thereafter, the temperature was raised to 95°C, and the mixture was heated while removing the alcohol out of the system until the alcohol generation ceased. The resin obtained was dissolved in methyl isobutyl ketone and the solution was stirred at room temperature for 1 day. Then, 0.83 mole of trimethylchlorosilane was added dropwise, followed by 1 hour of heating at 60°C. The mixture was washed with water until the washings of the resin became neutral. The organic phase separated was deprived of the solvent and low-molecular byproducts by evaporation to give an aromatic group-containing organosiloxane compound (A2) as a solid.

[0043]

- 30 (Production Example 3): Production of an aromatic group-containing organosiloxane compound (A3)

- A reaction vessel was charged with 1.0 mole of diphenyldimethoxysilane, 5.1 moles of pure water and 400 ppm of 35% hydrochloric acid, and the mixture was stirred at 60°C for 3 hours. Then, 1.0 mole of tetraethoxysilane

was added dropwise at 60°C. Thereafter, while removing the alcohol out of the system at 90°C, the temperature was raised to 120°C and the mixture was heated until alcohol generation was ceased. After cessation of the alcohol

5 generation, the mixture was stirred at 140°C for 2 hours. The resin obtained was dissolved in methyl isobutyl ketone, the solution was stirred at room temperature for 1 day, 1.5 moles of trimethylchlorosilane was then added dropwise, and the mixture was heated at 60°C for 1 hour. The mixture was
10 washed with water until the washings of the resin became neutral, the organic phase separated was deprived of the solvent and low-molecular byproducts by evaporation to give an aromatic group-containing organosiloxane compound (A3) as a solid.

15 [0044]

(Production Example 4): Production of an aromatic group-containing organosiloxane compound (A4)

An aromatic group-containing organosiloxane compound (A4) was obtained as a solid in the same manner as in
20 Production Example 1 except that 0.5 part of tetrachlorosilane, 21.5 parts of methyltrichlorosilane, 62.0 parts of phenyltrichlorosilane, 260 parts of methyl isobutyl ketone as solvent, 70 parts of ion-exchange water and 16.0 parts of trimethylchlorosilane were used.

25 [0045]

(Reference Production Example 1): Production of an aromatic group-containing organosiloxane compound (A'1)

A reaction vessel was charged with 1.0 part of tetrachlorosilane, 22.0 parts of methyltrichlorosilane,
30 62.0 parts of phenyltrichlorosilane and 180 parts of methyl isobutyl ketone as solvent with ice cooling, and 45 parts of ion-exchange water was added with stirring over 0.5 hour while adjusting the temperature within the range of 0 to 30°C. After completion of the addition, a gel-like matter
35 insoluble in the solvent formed. After 12 hours of

stirring at room temperature, 15.0 parts of trimethylchlorosilane was added dropwise at room temperature and the mixture was stirred at room temperature for 12 hours. The mixture was washed with water until the washings of the resin became neutral, followed by filtration and drying under vacuum to give an aromatic group-containing organosiloxane compound (A'1) as a solid. [0046]

(Reference Production Example 2): Production of an aromatic group-containing organosiloxane compound (A'2)

A reaction vessel was charged with 15.0 parts of methyltrichlorosilane, 80.0 parts of phenyltrichlorosilane and 180 parts of methyl isobutyl ketone as solvent with ice cooling, and 75 parts of ion-exchange water was added gradually with stirring over 1 hour while adjusting the temperature within the range of 0 to 20°C. After completion of the addition, the mixture was stirred at 60°C for 4 hours and then at room temperature for 12 hours, 5.0 parts of trimethylchlorosilane was added dropwise at room temperature and the mixture was stirred at room temperature for 12 hours. The mixture was washed with water until the washings of the resin became neutral, and the organic phase separated was deprived of the solvent and low-molecular byproducts by evaporation to give an aromatic group-containing organosiloxane compound (A'2) as a solid. [0047]

(Reference Production Example 3): Production of an aromatic group-containing organosiloxane compound (A'3)

A reaction vessel was charged with 85 parts of ion-exchange water and 250 parts of methyl isobutyl ketone as solvent with ice cooling and then 33.0 parts of methyltrichlorosilane and 51.0 parts of phenyltrichlorosilane were added gradually with stirring over 8 hours while adjusting the temperature within the range of 0 to 5°C. After completion of the addition, 16.0

parts of trimethylchlorosilane was added dropwise at room temperature and the mixture was stirred at room temperature for 12 hours. The mixture was washed with water until the washings of the resin became neutral. The organic phase separated was deprived of the solvent and low-molecular byproducts by evaporation to give an aromatic group-containing organosiloxane compound (A'3) as a solid.

[0048]

(Reference Production Example 4): Production of an aromatic group-containing organosiloxane compound (A'4)

A reaction vessel was charged with 1.5 moles of tetraethoxysilane, 3.0 moles of pure water, 3.0 moles of methanol and 40 ppm of 35% hydrochloric acid, and the reaction was carried out in the same manner as in

Production Example 2 and the resin was dissolved in the solvent as in Production Example 2. Thereafter, the same procedure of as in Production Example 2 was followed except that 2.0 moles of dimethylphenylchlorosilane was added dropwise to give an aromatic group-containing

organosiloxane compound (A'4) as a solid.

[0049]

(Reference Production Example 5): Production of an aromatic group-containing organosiloxane compound (A'5)

An aromatic group-containing organosiloxane compound (A'5) was obtained as a solid in the same manner as in Production Example 1 except that 31.0 parts of methyltrichlorosilane, 36.0 parts of phenyltrichlorosilane, 10.0 parts of diphenyldichlorosilane, 180 parts of methyl isobutyl ketone as solvent, 75 parts of ion-exchange water and 23.0 parts of trimethylchlorosilane were used.

[0050]

(Reference Production Example 6): Production of an aromatic group-containing organosiloxane compound (A'6)

An aromatic group-containing organosiloxane compound (A'6) was obtained as a solid in the same manner as in

Reference Production Example 3 except that 120 parts of ion-exchange water, 300 parts of methyl isobutyl ketone as solvent, 0.5 part of tetrachlorosilane, 64.0 parts of methyltrichlorosilane, 15.5 parts of phenyltrichlorosilane, and 20.0 parts of trimethylchlorosilane were used.

[0051]

(Reference Production Example 7): Production of an aromatic group-containing organosiloxane compound (A'7)

An aromatic group-containing organosiloxane compound (A'7) was obtained as a solid in the same manner as in Production Example 1 except that 5.0 parts of tetrachlorosilane, 65.0 parts of phenyltrichlorosilane, 200 parts of methyl isobutyl ketone as solvent, 75 parts of ion-exchange water and 30.0 parts of dimethylphenylchlorosilane were used.

The results of analysis of each aromatic group-containing organosiloxane compound are shown in Table 1, and the silane compounds used in the synthesis are shown in Table 2.

[0052]

[Table 1]

Sample name	m+n	n/m	Number average mol. wt. (Mn)	Mol. wt. distribution (Mw/Mn)	Fluidity at 23°C	Fluidity at 200°C	Solubility in 1L of toluene	Gelation at 200°C
A1	1.24	1.27	3440	1.67	Nonfluid	Fluid	>200g	No gelation
A2	1.53	0.47	3030	1.46	Nonfluid	Fluid	>200g	No gelation
A3	1.47	1.08	4880	4.38	Nonfluid	Fluid	>200g	No gelation
A4	1.31	0.75	4410	4.28	Nonfluid	Fluid	>200g	No gelation
A'1	Unmeasurable	Unmeasurable	Unmeasurable	Unmeasurable	Nonfluid	Nonfluid	1.5g	Not tested
A'2	1.33	1.22	5380	9.29	Nonfluid	Fluid	>200g	Gelation
A'3	1.37	0.45	2520	1.33	Fluid	Fluid	>200g	No gelation
A'4	1.08	0.5	5750	13.5	Nonfluid	Fluid	>200g	No gelation
A'5	1.75	0.61	6820	10.87	Nonfluid	Fluid	>200g	No gelation
A'6	1.23	0.12	3450	2.32	Nonfluid	Fluid	>200g	No gelation
A'7	1.19	2.55	5010	4.67	Nonfluid	Fluid	>200g	No gelation

[0053]

In Table 1, "unmeasurable" means that the sample was not dissolved in chloroform, so that each analysis could not be carried out.

5 [0054]

[Table 2]

Sample name	Silane compound used in synthesis
A1	Tetrachlorosilane, phenyltrichlorosilane, methyltrichlorosilane, trimethylchlorosilane
A2	Tetraethoxysilane, phenyltrimethoxysilane, trimethylchlorosilane
A3	Tetraethoxysilane, diphenyldimethoxysilane, trimethylchlorosilane
A4	Tetrachlorosilane, phenyltrichlorosilane, methyltrichlorosilane, trimethylchlorosilane
A'1	Tetrachlorosilane, phenyltrichlorosilane, methyltrichlorosilane, trimethylchlorosilane
A'2	Phenyltrichlorosilane, methyltrichlorosilane, trimethylchlorosilane
A'3	Phenyltrichlorosilane, methyltrichlorosilane, trimethylchlorosilane
A'4	Tetraethoxysilane, dimethylphenylchlorosilane
A'5	Phenyltrichlorosilane, methyltrichlorosilane, diphenyldichlorosilane, trimethylchlorosilane
A'6	Tetrachlorosilane, phenyltrichlorosilane, methyltrichlorosilane, trimethylchlorosilane
A'7	Tetrachlorosilane, phenyltrichlorosilane, dimethylphenylchlorosilane

[0055]

(Example 1)

An aromatic bisphenol A-type polycarbonate (TARFLON A-2200; product of Idemitsu Petrochemical; 100 parts), 3
5 parts of the aromatic group-containing organosiloxane compound (A1) produced in Production Example 1, 0.3 part of a tetrafluoroethylene (POLYFLON FA-500; product of Daikin Industries), 0.1 part of a phenolic stabilizer (ADK STAB AO-60; product of Asahi Denka Kogyo) and 0.1 part of a
10 phosphite stabilizer (ADK STAB HP-10; product of Asahi Denka Kogyo) were blended, and the raw material mixture was charged into the hopper of a unidirectional twin-screw extruder with a tip temperature maintained at 280°C and melt-kneaded to give a resin composition.

15 [0056]

(Examples 2 to 6 and Comparative Examples 1 to 7)

Resin compositions were prepared in the same manner as in Example 1. The resin(s) and aromatic group-containing organosiloxane compound used were varied as
20 shown in Table 3.

The resins used were as follows:

PET: Polyethylene terephthalate resin with a logarithmic viscosity of 0.70.

25 PPE: Poly(2,6-dimethyl-1,4-phenylene) ether resin with a logarithmic viscosity of 0.50.

HIPS: Styrene-butadiene copolymer (Estyrene HI H-65; product of Nippon Steel Chemical).

ABS: Styrene-acrylonitrile-butadiene copolymer (Kaneka MUH 85000H; product of Kaneka Corporation).

30 [0057]

Evaluation method 1: Flame retardancy

Bars, 1.6 mm thick, 12.7 mm wide and 127 mm long, were prepared from the pellets obtained and evaluated for flame retardancy of bars with 1.6 mm thick according to the
35 UL-94 V standard.

[0058]

Evaluation method 2: Dispersed particle diameter

Bars, 3.2 mm thick, 12.7 mm wide and 127 mm long, were prepared from the pellets obtained, and were sliced from the middle portion thereof in the direction of thickness, the section thereof was observed under a transmission electron microscope and the number average dispersed particle diameter was calculated by image processing.

The evaluation results are shown in Table 3.

[0059]

[Table 3]

15

20

25

30

35

		Resin					Organosiloxane compound		UL94	Dispersed particle diameter (μm)
		PC	PET	PPE	HIPS	ABS	Sample name	Addition level		
Example	1	100	—	—	—	—	A1	3	V-0	0.11
	2	80	20	—	—	—	A1	3	V-0	0.12
	3	90	10	—	—	—	A2	3	V-0	0.25
	4	90	10	—	—	—	A3	3	V-0	0.22
	5	90	10	—	—	—	A4	3	V-0	0.16
	6	—	—	90	10	—	A1	6	V-0	0.27
	7	90	—	—	—	10	A1	6	V-0	0.26
Compar. Ex.	1	100	—	—	—	—	A'1	3	Off-grade	2.41
	2	90	10	—	—	—	A'2	3	Off-grade	0.55
	3	90	10	—	—	—	A'3	3	Off-grade	0.09
	4	90	10	—	—	—	A'4	3	Off-grade	0.42
	5	90	10	—	—	—	A'5	3	Off-grade	0.33
	6	100	—	—	—	—	A'6	3	Off-grade	0.52
	7	90	10	—	—	—	A'7	3	Off-grade	0.17

[0060]

The transmission electron photomicrograph obtained in Example 1 is attached hereto as Fig. 1, the transmission electron photomicrograph obtained in Example 2 as Fig. 2, the transmission electron photomicrograph obtained in Comparative Example 1 as Fig. 3, and the transmission electron photomicrograph obtained in Comparative Example 6 as Fig. 4. In Fig. 1, the aromatic group-containing organosiloxane compound A1 is seen dispersed as deep black spots in the gray PC. In Fig. 2, the aromatic group-containing organosiloxane compound A1 is seen dispersed as deep black spots and the PET as white spots in the gray PC. In Fig. 3, the aromatic group-containing organosiloxane compound A'1 is seen dispersed as dense spots in the gray PC. In Fig. 4, the aromatic group-containing organosiloxane compound A'6 is seen dispersed as pale gray spots in the gray PC.

[0061]

As is evident from Table 3, good flame retardancy was obtained in all Examples in which the flame retardant according to the present invention was used whereas, in the Comparative Examples in which the flame retardant used was outside the scope of the present invention, the flame retardancy was poor in any case. In all Examples, each aromatic group-containing organosiloxane compound was finely dispersed whereas, in the Comparative Examples, the dispersed particle diameter was too large or too small.

[0062]

[Effect of the Invention]

As shown hereinabove, it is seen that the resin composition in which the flame retardant of the present invention is used can provide good flame retardancy as a result of mere addition of a small amount of the aromatic group-containing organosiloxane compound without using any halogen compound or phosphorus compound. These are

industrially very useful.

[Brief Description of the Drawings]

[Fig. 1] A transmission electron photomicrograph of the section of a bar obtained from the composition of Example 1.

5 [Fig. 2] A transmission electron photomicrograph of the section of a bar obtained from the composition of Example 2.

[Fig. 3] A transmission electron photomicrograph of the section of a bar obtained from the composition of Comparative Example 1.

10 [Fig. 4] A transmission electron photomicrograph of the section of a bar obtained from the composition of Comparative Example 6.

15

20


25

30


35

[Document Name] Drawings

[Fig. 1]



[Fig. 2]




BEST AVAILABLE COPY

[Fig. 3]



[Fig. 4]



BEST AVAILABLE COPY


[Document Name] Abstract

[Abstract]

[Subject] To provide flame retardants which can provide high flame retardancy by means of silicon compounds.

[Means for Solving] A flame retardant comprising an aromatic group-containing organosiloxane compound

wherein said compound has the following mean composition formula (1), does not flow at 23°C, flows at 200°C, does not gelate when heated at 200°C with stirring for 30 minutes, has a number average molecular weight of not less than 2,000 and at the same time, dissolves not less than 100 g in 1 L of a solvent toluene at 23°C:



in the formula, R^1 represents a univalent aliphatic hydrocarbon group containing 1 to 4 carbon atoms; R^2 represents a univalent aromatic hydrocarbon group containing 6 to 24 carbon atoms; R^1 and R^2 each may contain two or more species; and m and n are numbers satisfying $1.1 \leq m + n \leq 1.7$ and $0.4 \leq n/m \leq 2.5$.

[Selective Figure] none